

16. The mineral wool product according to claim 7, wherein the weight per surface unit of said fiber mat (3) is 40 to 80 g/m².
17. The mineral wool product according to claim 7, wherein the weight per surface unit of said fiber mat (3) is approx. 60 g/m².
18. The process according to claim 8, wherein an application quantity of approx. 300 g/m² of foamed coating mass is used.
19. The process according to claim 8, wherein a foam weight per liter of approx. 250 g/l is used.
20. The process according to claim 8, wherein said layer (2) is dried in a tunnel furnace at temperature of approx. 260°C.

REMARKS

The specification claims have been amended to conform the original translated specification and claims to U.S. requirements, i.e., appropriate section headers are added, reference in the specification to the claims have been amended in order to eliminate multiple dependent claims and claims improperly depending from multiple dependent claims, and to otherwise conform the claims to U.S. practice. Care has been taken to ensure that no new matter is added to the text.